



C110 Copper Alloy Wire

Introduction

C110 is a commercial copper which is more economical than C102. It has good solderability and corrosion resistance and is used for high current applications.

To learn more please contact our [sales department](#).

C110 Copper Alloy Wire

Chemical Composition - Limits		Chemical Composition - Nominal	
Cu 99.90 min - incl Ag		Cu 99.90	
		O 0.04	
Specifications		Fabrication Index	
ASTM B1		Soldering	5 - Excellent
ASTM B2		Hot Worked	5 - Excellent
ASTM B3		Cold Worked	5 - Excellent
ASTM B33		Brazing	4 - Very Good
ASTM B48		Machinability	1 - Poor
ASTM B152			
ASTM B246			
ASTM B272			
ASTM B298			
ASTM B355			

Physical Properties

Annealing Range (Min)	700 °F
Annealing Range (Max)	1200 °F
Density	0.322 lb/in ³
Electrical Resistivity (Annealed)	10.3 Ω·cir-mil/ft @ 68 °F
Electrical Conductivity (Annealed)	101% IACS @ 68 °F
Thermal Conductivity	226 Btu/ft ² /ft·hr/°F @ 68 °F
Coefficient of Thermal Expansion	9.8 per °F (68-572 °F)
Modulus of Elasticity (Tension)	17 ksi
Modulus of Rigidity (Tension)	6 ksi
Melting Point (Solidus)	1,700 °F

C110 Copper Alloy Wire

Melting Point (Liquidus)

1,900 °F

Fisk Alloy Wire Inc.
P.O. Box 26
10 Thomas Road N.
Hawthorne, NJ 07506 U.S.A.

Phone: (973) 825-8500
Fax: (973) 427-4585
E-mail: sales@fiskalloy.com

©2024 Fisk Alloy Wire Inc.
Percon is a registered
trademark of Fisk Alloy
Wire Inc.
Information provided on
this page is for reference
purposes only.

C110 Copper Alloy Wire

Round Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Typical		
Annealed	OS050	35.0		.0010 - .1285 inch
Hard Drawn	H04	60.0		

Square Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Typical		
Annealed	OS050	35.0		.0100 - .0808 inch
Hard Drawn	H04	60.0		

Rolled Flat

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
Annealed	OS050	26.0	38.0	Thickness: .0100 - .0500 inch
1/4 Hard	H01	34.0	42.0	
1/2 Hard	H02	37.0	46.0	Width: .0150 - .2500 inch
Hard	H04	43.0	52.0	
Spring	H08	50.0	58.0	