



## **C18150** Copper Chromium Zirconium

---

Fisk Alloy Wire Inc.  
P.O. Box 26  
10 Thomas Road N.  
Hawthorne, NJ 07506 U.S.A.

Phone: (973) 825-8500  
Fax: (973) 427-4585  
E-mail: [sales@fiskalloy.com](mailto:sales@fiskalloy.com)

©2024 Fisk Alloy Wire Inc.  
Percon is a registered  
trademark of Fisk Alloy  
Wire Inc.  
Information provided on  
this page is for reference  
purposes only.

# C18150 Copper Chromium Zirconium

Chemical Composition - Limits	Chemical Composition - Nominal
Cu rem - incl Ag (99.7 min incl named elements)	Cu 98.9
Cr 0.50-1.5	Cr 1.0
Zr 0.02-0.20	Zr 0.11

  

Fabrication Index	
Soldering	5 - Excellent
Hot Worked	5 - Excellent
Cold Worked	5 - Excellent
Brazing	4 - Very Good
Machinability	1 - Poor

## Physical Properties

Annealing Range (Min)	1800 °F
Annealing Range (Max)	1850 °F
Density	0.321 lb/in <sup>3</sup>
Electrical Resistivity (Annealed)	13 Ω·cir-mil/ft @ 68 °F
Electrical Conductivity (Annealed)	80% IACS @ 68 °F
Thermal Conductivity	187 Btu/ft <sup>2</sup> /ft·hr/°F @ 68 °F
Coefficient of Thermal Expansion	9.5 per °F (68-572 °F)
Modulus of Elasticity (Tension)	17 ksi
Melting Point (Solidus)	1,700 °F
Melting Point (Liquidus)	1,900 °F

# C18150 Copper Chromium Zirconium

## Round Rod - Pretempered

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)	
		Min	Max
AT	TFO0	65.0	80.0
1/8 Hard	TL00	70.0	85.0
1/4 Hard	TL01	75.0	90.0
1/2 Hard	TL02	80.0	95.0
Hard	TL04	85.0	100
Spring	TL08	90.0	105
Extra Spring AT	TL10	100	