



C197 High Performance Alloy Wire

Introduction

Alloy C197 is a high conductivity copper alloy possessing an excellent combination of strength, conductivity and softening resistance. This alloy can be substituted for medium tempers of brass and bronze when higher electrical conductivity is required or better solderability is needed. Alloy C197 is an improved version of alloy C194 and has substantially greater conductivity at the same strength levels.

To learn more please contact our [sales department](#).

C197 High Performance Alloy Wire

Chemical Composition - Limits	Chemical Composition - Nominal
Cu rem (99.8 min incl named elements)	Cu 99.0
Fe 0.30-1.2	Fe 0.70
Mg 0.01-0.20	P 0.25
P 0.10-0.40	Mg 0.10
Mn 0.05 max	
Ni 0.05 max	
Pb 0.05 max	
Sn 0.20 max	
Zn 0.20 max	
Co 0.05 max	
Specifications	Fabrication Index
ASTM B465	Soldering 5 - Excellent
	Hot Worked 5 - Excellent
	Cold Worked 5 - Excellent
	Brazing 5 - Excellent
	Machinability 1 - Poor

Physical Properties

Annealing Range (Min)	700 °F
Annealing Range (Max)	1200 °F
Density	0.319 lb/in ³
Electrical Resistivity (Annealed)	13 Ω·cir-mil/ft @ 68 °F
Electrical Conductivity (Annealed)	80% IACS @ 68 °F
Thermal Conductivity	150 Btu/ft ² /ft·hr/°F @ 68 °F
Coefficient of Thermal Expansion	9.7 per °F (68-572 °F)

C197 High Performance Alloy Wire

Modulus of Elasticity (Tension)	17 ksi
Modulus of Rigidity (Tension)	6 ksi
Melting Point (Solidus)	1,700 °F
Melting Point (Liquidus)	1,900 °F

C197 High Performance Alloy Wire

Round Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
Annealed		39.0	47.0	.0010 - .1285 inch
1/4 Hard	H01	50.0	65.0	
1/2 Hard	H02	60.0	75.0	
3/4 Hard	H03	70.0	85.0	
Hard	H04	80.0	95.0	
Spring	H08	90.0		

Square Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
Annealed		39.0	47.0	.0100 - .0808 inch
1/4 Hard	H01	50.0	65.0	
1/2 Hard	H02	60.0	75.0	
3/4 Hard	H03	70.0	85.0	
Hard	H04	80.0	95.0	
Spring	H08	90.0		

Rolled Flat

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	

C197 High Performance Alloy Wire

Rolled Flat

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
1/2 Hard	H02	53.0	63.0	.0150 - .2500 inch
Annealed Hard	O60 H04	43.0 60.0	53.0 70.0	
Spring	H08	70.0	76.0	Thickness: .0100 - .0500 inch

Width: