



C21000 Gilding, 95%

Fisk Alloy Wire Inc.
P.O. Box 26
10 Thomas Road N.
Hawthorne, NJ 07506 U.S.A.

Phone: (973) 825-8500
Fax: (973) 427-4585
E-mail: sales@fiskalloy.com

©2024 Fisk Alloy Wire Inc.
Percon is a registered
trademark of Fisk Alloy
Wire Inc.
Information provided on
this page is for reference
purposes only.

C21000 Gilding, 95%

Chemical Composition - Limits		Chemical Composition - Nominal	
Cu 94.0-96.0 (99.8 min incl named elements)		Cu 95	
Zn rem		Zn 5	
Pb 0.05 max			
Fe 0.05 max			
Specifications		Fabrication Index	
ASTM B36		Soldering	5 - Excellent
ASTM B134		Hot Worked	4 - Very Good
		Cold Worked	5 - Excellent
		Brazing	5 - Excellent
		Machinability	1 - Poor

Physical Properties

Annealing Range (Min)	800 °F
Annealing Range (Max)	1450 °F
Density	0.32 lb/in ³
Electrical Resistivity (Annealed)	18.5 Ω -cir-mil/ft @ 68 °F
Electrical Conductivity (Annealed)	56% IACS @ 68 °F
Thermal Conductivity	135 Btu/ft ² /ft-hr/°F @ 68 °F
Coefficient of Thermal Expansion	10 per °F (68-572 °F)
Modulus of Elasticity (Tension)	17 ksi
Modulus of Rigidity (Tension)	6 ksi
Melting Point (Solidus)	1,620 °F
Melting Point (Liquidus)	1,880 °F

Round Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
1/8 Hard	H00	35.0	45.0	.0010 - .1285 inch
1/4 Hard	H01	41.0	51.0	
1/2 Hard	H02	49.0	58.0	
3/4 Hard	H03	57.0	64.0	
Hard	H04	61.0	68.0	
Extra Hard	H06	66.0	73.0	
Spring	H08	72.0		

Square Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
1/8 Hard	H00	35.0	45.0	.0100 - .0808 inch
1/4 Hard	H01	41.0	51.0	
1/2 Hard	H02	49.0	58.0	
3/4 Hard	H03	57.0	64.0	
Hard	H04	61.0	68.0	
Extra Hard	H06	66.0	73.0	
Spring	H08	72.0		

Rolled Flat

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	

C21000 Gilding, 95%

Rolled Flat

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
1/2 Hard	H02	42.0	52.0	.0100 - .0500 inch
3/4 Hard	H03	46.0	56.0	Width: .0150 - .2500 inch
Hard	H04	50.0	59.0	Thickness:
1/4 Hard	H01	37.0	47.0	
Extra Hard	H06	56.0	64.0	
Spring	H08	60.0	68.0	