



C521 Bronze Alloy Wire

Introduction

Alloy C521 is a high tin alloy of the phosphor bronze family. The additional tin relative to the more commonly used C510 results in higher mechanical properties with a modest reduction in electrical conductivity. Applications include electronic parts, springs, contacts, switch parts and fasteners.

To learn more please contact our [sales department](#).

C521 Bronze Alloy Wire

Chemical Composition - Limits		Chemical Composition - Nominal	
Cu rem (99.5 min incl named elements)		Cu 92.0	
Sn 7.0-9.0		Sn 8.0	
Pb 0.05 max		P 0.20	
Zn 0.20 max			
Fe 0.10 max			
P 0.03-0.35			
Specifications		Fabrication Index	
ASTM B103		Soldering	5 - Excellent
ASTM B159		Hot Worked	2 - Fair
		Cold Worked	4 - Very Good
		Brazing	5 - Excellent
		Machinability	1 - Poor

Physical Properties

Annealing Range (Min)	900 °F
Annealing Range (Max)	1250 °F
Density	0.318 lb/in ³
Electrical Resistivity (Annealed)	79.8 Ω·cir-mil/ft @ 68 °F
Electrical Conductivity (Annealed)	13% IACS @ 68 °F
Thermal Conductivity	36 Btu/ft ² /ft·hr/°F @ 68 °F
Coefficient of Thermal Expansion	10.1 per °F (68-572 °F)
Modulus of Elasticity (Tension)	16 ksi
Modulus of Rigidity (Tension)	6 ksi
Melting Point (Solidus)	1,620 °F
Melting Point (Liquidus)	1,880 °F

C521 Bronze Alloy Wire

Round Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
Annealed		53.0	68.0	.0010 - .1285 inch
1/4 Hard	H01	74.0	91.0	
1/2 Hard	H02	95.0	115	
3/4 Hard	H03	113	135	
Hard	H04	125	150	

Square Wire

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
Annealed		53.0	68.0	.0100 - .0808 inch
1/4 Hard	H01	74.0	91.0	
1/2 Hard	H02	95.0	115	
3/4 Hard	H03	113	135	
Hard	H04	125	150	

Rolled Flat

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
Annealed		53.0	67.0	Thickness: .0100 - .0500 inch
1/2 Hard	H02	69.0	84.0	
Hard	H04	85.0	100	Width: .0150 - .2500 inch
Extra Hard	H06	97.0	112	
Spring	H08	105	119	

C521 Bronze Alloy Wire

Rolled Flat

TEMPER NAME	TEMPER CODE	TENSILE STRENGTH (ksi)		MILL LIMITS (inch)
		Min	Max	
Extra Spring	H10	110	122	